(19) World Intellectual Property Organization International Bureau





(43) International Publication Date 21 May 2004 (21.05.2004)

PCT

(10) International Publication Number WO 2004/042717 A1

(51) International Patent Classification7:

G11B 7/24

(21) International Application Number:

PCT/IB2003/004682

(22) International Filing Date: 22 October 2003 (22.10.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

6 November 2002 (06.11.2002)

02079629.8 02080572.7 30 December 2002 (30.12.2002)

(71) Applicant (for all designated States except US): KONIN-KLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).


- (72) Inventors; and
- (75) Inventors/Applicants (for US only): VAN SCHLJNDEL, Mark [NL/NL]; c/o Prof. Holstlaan 6, NL-5656 AA

Eindhoven (NL). MARTENS, Hubert C., F. [NL/NL]; c/o Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). TIEKE, Benno [DE/NL]; c/o Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). ZHOU, Guofu [NL/NL]; c/o Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).

- (74) Agent: DEGUELLE, Wilhelmus, H., G.; Philips Intellectual Property & Standards, Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,

[Continued on next page]

(54) Title: MULTI-STACK OPTICAL DATA STORAGE MEDIUM AND USE OF SUCH MEDIUM



(57) Abstract: The present invention relates to a multi-stack optical data storage medium (10). The medium comprises a first substrate (1a) with present on a side thereof a first recording stack (13) named Lo, a second substrate (1b) with present on a side thereof a second recording stack (12) named L1 comprising a recordable type L1 recording layer (4) having a thickness t_{RL1} and a complex refractive index n_{λ} - i* k_{λ} at a wavelength λ . A second reflective layer (6) is present adjacent the L_1 recording layer (4) at a side most remote from a radiation beam (20) entrance face (11) of the medium. The second recording stack L₁ (12) is present at a position closer to the entrance face (11) than the Lo recording stack (13). A radiation beam transparent spacer layer (9) is sandwiched between the recording stacks (12, 13). In order to achieve compatibility with the DVD-9 ROM standard as far as reflection levels are concerned, the second reflective layer (6) mainly comprises the metal Cu and has a thickness t_{MLn} selected from the range of 8 - 20 nm and the thickness t_{RL1} and k_{λ} of the recordable L_1 recording layer (4) fulfils the formula $t_{RL1} * k_{\lambda} \le 8$ nm.